

Code No.01-0164

SPECIFICATION

Alumina B-10
for TLC

REQUIREMENT	SPECIFICATION
Appearance	White ~ nearly white, powder
Particle size (finer than 45 μm)	min.75.0%
Loss on drying at 105°C	max.5.0%
pH(100g/l aqueous slurry,25°C)	7.0~9.0
Practical test	to pass test
Binder (CaSO ₄ · 0.5H ₂ O)	10~12%