## **SPECIFICATION**

## Alumina B-10F

for Thin Layer Chromatography

REQUIREMENT	SPECIFICATION
Appearance	White $\sim$ nearly white, powder
Particle size (pass 45 μm)	min.75.0%
Loss on drying at 105℃	under investigation
pH(100g/l aqueous slurry,25°C)	7.0~9.0
Practical test	to pass test
Binder (CaSO4 · 0.5H2O)	10~12%

(1 / 1) revised on 2010/08/19