

Code No.03-0169

SPECIFICATION

Cellulose Acetate

REQUIREMENT	SPECIFICATION
Appearance	White ~ nearly white, powder or flakes
Solubility in acetone	to pass test
Loss on drying at 105°C	max.5.0%
Acetylation degree (after drying)	53~56%
Acetyl group (after drying)	38~40%