

Code No.03-1625

# SPECIFICATION

## Copper

Reference Material for Volumetric Analysis

| REQUIREMENT   | SPECIFICATION          |
|---------------|------------------------|
| * Appearance  | Reddish brown turnings |
| Assay         | min.99.98%(mass/mass)  |
| Silver (Ag)   | to pass test           |
| Lead (Pb)     | max.5ppm(mass/mass)    |
| Arsenic (As)  | max.5ppm(mass/mass)    |
| Antimony (Sb) | max.5ppm(mass/mass)    |
| Bismuth (Bi)  | max.5ppm(mass/mass)    |
| Sulfur (S)    | max.0.002%(mass/mass)  |
| Iron (Fe)     | max.5ppm(mass/mass)    |
| Nickel (Ni)   | max.5ppm(mass/mass)    |

JIS K 8005:2006

\*:Additional test performed by Wako but not required by JIS