

SPECIFICATION

Charcoal, Activated, Broken, 0.2~1 mm for Column Chromatography

REQUIREMENT	SPECIFICATION
Appearance	Black shot
Particle shape	Irregular
Particle size (0.21~1mm)	min.70%
Loss on drying at 130°C	max.15.0%
pH (40g/l aqueous slurry,25°C)	8.0~11.0
Iodine adsorption power	to pass test