

Code No.05-0219

## SPECIFICATION

## Ethyl Cellulose (abt.49% ethoxy) 10

| REQUIREMENT   | SPECIFICATION |
|---|---------------|
| Appearance  | to pass test  |
| Viscosity (5%, 25°C) (after drying)   | 8~14mPa·s     |
| Loss on drying at 105°C   | max.5.0%      |
| Ethoxy group (C <sub>2</sub> H <sub>5</sub> O-) (calculated on the dried basis) | 45~50%        |