SPECIFICATION

Gelatin, from Bovine Bone

for Biochemistry

REQUIREMENT	SPECIFICATION
Appearance Viscosity	White ∼ pale yellowish brown、 shot or powder 4.2∼5.2mPa·s
Solubility in water	to pass test
Loss on drying at 105℃	max.15.0%
pH of a 50g/I solution at 35℃	5.5~6.5
Heavy metals (as Pb)	max.0.005%
Arsenic (As)	max.1ppm
Jelly strength	240~280g/cm2

(1 / 1) revised on 2013/06/20