

Code No.16-0305

## SPECIFICATION

## Polyvinyl Alcohol (Polymerization Degree about 1500)

REQUIREMENT	SPECIFICATION
Appearance	to pass test
Viscosity (40g/L, 25°C) (after drying)	18~25mPa·s
Solubility in water	to pass test
Loss on drying at 105°C	max.5.0%
pH of a 50g/L solution at 25°C	5.0~8.0
Saponification degree	86.0~90.0mol%