

SPECIFICATION

Polyvinyl Alcohol n=1500~1800

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	to pass test
Viscosity (4%, 20°C) (calculated on the dried basis)	25~33mPa·s
Solubility in water	to pass test
Loss on drying at 105°C	max.6.0%
pH of a 50g/L solution at 25°C	5.0~7.5
Saponification degree	min.98.0mol%
Polymerization degree	under investigation