

SPECIFICATION

Poly(vinyl alcohol) 500, Completely Hydrolyzed

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	White ~ slightly yellow, crystals
Viscosity (4%, 20°C) (calculated on the dried basis)	under investigation
Solubility in water	to pass test
Loss on drying at 105°C	max.6.0%
pH of a 50g/l solution at 25°C	5.0~7.5
Saponification degree	min.96.0mol%
Polymerization degree	under investigation