

Code No.16-1852

SPECIFICATION

Polyethylene Glycol 500,000

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	White ~ slightly yellow, crystalline powder ~ powder or granules
Viscosity (2%, 25°C)	40~100mPa·s
Solubility in water	to pass test
Loss on drying at 105°C	max.5.0%
Residue after ignition (as sulfate)	max.2.0%
pH of a 20g/l solution at 25°C	6.0~8.0
Acidity (as CH ₃ COOH)	max.0.2%