

Code No.18-0108

SPECIFICATION

Ruthenium(IV) Oxide Practical Grade

REQUIREMENT	SPECIFICATION
Appearance	Black powder
Loss on drying at 105°C	max.0.3%