SPECIFICATION

Wakogel(R) Q-63, through 45μ m (325mesh)

for Column Chromatography

REQUIREMENT	SPECIFICATION
Appearance	White powder
Particle size (pass 45 μm)	min.80%
Precipitation volume	1.5~2.5ml/g
Loss on drying at 150℃	max.10.0%
pH(100g/l aqueous slurry,25°C)	4.0~6.0
Practical test	to pass test

(1 / 1) revised on 2015/11/13