

Code No.23-0078

SPECIFICATION

WE174

for Electron Microscopy

REQUIREMENT	SPECIFICATION
Appearance	Colorless ~ slightly yellow, clear liquid
Viscosity (25°C)	15~35mPa·s
Solubility in NSA	to pass test
Density (20°C)	1.18~1.20g/ml
Water	max.0.5%
Practical test	to pass test
Epoxy equivalent	125~135