

Code No.08-0386

SPECIFICATION

Hydroxypropyl Cellulose 150~400 cP

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	White ~ slightly yellowish brown, crystalline powder ~ powder
Viscosity (20g/l, 20°C)	150~400cP
Loss on drying at 105°C	max.5.0%
Residue after ignition (as sulfate)	max.0.5%
pH of a 20g/l solution at 25 °C	5.0~7.5