

Code No.16-1791

SPECIFICATION

Polyvinyl Alcohol

Guaranteed Reagent

REQUIREMENT	SPECIFICATION
* Appearance Solubility in water Loss on drying at 105°C Residue after ignition (as sulfate) Viscosity (4%, 20°C) Suitability for absorptiometric determination Saponification degree	White ~ slightly yellow, shot ~ powder to pass test max.10.0%(mass/mass) max.1.0%(mass/mass) 35~55mPa·s to pass test 78~82mol%

JIS K 9550 : 2020(*:Additional test performed by Wako but not required by JIS)