

Code No.03-1612

SPECIFICATION

Chitosan 10

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	to pass test
Viscosity (5g/l, 20°C) (after drying)	max.20mPa·s
Solubility in dil.acetic acid	to pass test
Loss on drying at 105°C	max.10.0%
pH (10g/l aqueous slurry,25°C)	8.0~10.0
Deacetylation rate (after drying)	min.80.0mol%