

Code No.03-2032

SPECIFICATION

Chitosan 50

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	to pass test
Viscosity (5g/l, 20°C) (after drying)	10~100mPa·s
Solubility in dil.acetic acid	to pass test
Loss on drying at 105°C	max.10.0%
pH (10g/l aqueous slurry,25°C)	7.0~9.0
Deacetylation rate (after drying)	min.80.0mol/mol%