

Code No.07-0384

# SPECIFICATION

## Graphite, Powder

Wako Special Grade

REQUIREMENT	SPECIFICATION
Appearance	Dark grayish black powder
Particle size (pass 45 $\mu$ m)	min.95%
Loss on drying at 105°C	max.0.4%
Residue after ignition	max.0.8%
Loss on ignition at 950°C	max.0.8%
Assay	min.98.0%