

Code No.13-0215

## SPECIFICATION

## Methyl Cellulose 4,000

Practical Grade

REQUIREMENT	SPECIFICATION
Appearance	White ~ slightly brown, powder
Viscosity (2%, 20°C) (calculated on the dried basis)	3,500~5,600mPa·s
Solubility in water	to pass test
Loss on drying at 105°C	max.5.0%
Residue after ignition	max.1.0%
Methoxy group (CH <sub>3</sub> O-) (calculated on the dried basis)	26~33%