

Code No.13-0503

SPECIFICATION

Methyl Cellulose 25

Practical Grade

REQUIREMENT	SPECIFICATION
Appearance	White ~ slightly brown, powder
Viscosity (2%, 20°C) (calculated on the dried basis)	20~30mPa·s
Solubility in water	to pass test
Loss on drying at 105°C	max.5.0%
Residue after ignition	max.1.0%
Methoxy group (CH ₃ O-) (calculated on the dried basis)	26~33%