## **SPECIFICATION**

## Polyvinylpyrrolidone K90

REQUIREMENT	SPECIFICATION
Appearance Viscosity (50g/l, 20°C) (calculated on the dried	White $\sim$ slightly yellow, crystalline powder $\sim$ powder $50\sim$ 90mPa $\cdot$ s
basis) Loss on drying at 105℃	max.5.0%
Heavy metals (as Pb)	max.0.001%
Arsenic (as As2O3)	max.2ppm
Total nitrogen (N) (after drying)	12.0~12.7%

(1 / 1) established on 2003/12/01