2024/04/25
Distributed by FUJIFILM Wako Pure Chemical Corporation
Manufactured by FUJIFILM Wako Pure Chemical Corporation

Code No.16-1128

SPECIFICATION

Polyethylene Glycol 20,000

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	White flakes
Viscosity (25%, 25℃)	50～200mPa･s
Solubility in water	to pass test
Freezing point	56～63℃
pH of a 50g/l solution at 25℃	4.5～7.5
Average molecular weight	15000～25000

revised on 2009/12/21