

Code No.20-0909

## SPECIFICATION

## 7,7,8,8-Tetracyanoquinodimethane

REQUIREMENT	SPECIFICATION
Appearance	Reddish yellow ~ yellowish brown, crystals
Melting point	292~295°C
Loss on drying over silica gel in vacuum	under investigation
Assay (HPLC)	min.98.5%