

Code No.03-2222

## SPECIFICATION

Cellulose, Powder, through 38  $\mu$  m (400mesh)

Wako 1st Grade

REQUIREMENT	SPECIFICATION
Appearance	White powder
Particle size (pass 38 $\mu$ m)	min.80%
Loss on drying at 105°C	max.7.0%
Residue on ignition	max.0.3%
pH(100g/L aqueous slurry, 25°C)	5.0~7.5